

GRADE	TRS (N/m m ²)	Density (g/cm ³)	Hardness (HRA)	ISO
ZG3X/ZG3	1600	15.0~15.3/14.9~15.3	91.5/91	K01
ZG6X/ZG6A	2000	14.6~15.0	91/92	K10
ZK6	3000 *	14.8~15.0	93	K10
ZG6	1800	14.8~15.0	90/91	K20
ZG8	2000	14.6~14.8	89.5	K30
ZK10S	3500~4000 *	14.4~14.6	91.5	K30
ZK10.8S	3000~3500 *	14.6~14.8	92.3	K30
ZG4C	1800	14.9~15.2	89.5	G05
ZG9C	2800 *	14.6~14.8	88	G10
ZG11C	3000 *	14.2~14.4	87.5	G30
ZG15	3000 *	14.0~14.2	87.5	LS40
ZG15C	3000 *	13.9~14.2	86.5	LT10
ZG20	3000 *	13.4~13.8	86.5	LQ30
ZG20C	3500 *	≥13.4	84	LT20
ZG25	3500 *	13.0~13.4	84	LQ30
ZT15	1400	11.5	≥91.5	P10
ZT14	1600	11.7	≥90.5	P20
ZT5	2000	12.8	≥89.5	P30
ZP40	2000	11	89.5	M30
ZP40A	2200	11.5	88	M30